

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
8 April 2004 (08.04.2004)

PCT

(10) International Publication Number
WO 2004/029538 A1

(51) International Patent Classification⁷: F41H 1/08, 5/04

(21) International Application Number:
PCT/IL2003/000782

(22) International Filing Date:
30 September 2003 (30.09.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
152006 30 September 2002 (30.09.2002) IL

(71) Applicant (for all designated States except US): RABIN-
TEX INDUSTRIES LTD. [IL/IL]; 28 Lechi Street, 51200
Bnei-Brak (IL).

(72) Inventor; and

(75) Inventor/Applicant (for US only): KAPAH, Yoav [IL/IL];
P.O.Box 389, 10600 Nahalal (IL).

(74) Agent: REINHOLD COHN AND PARTNERS; P.O.Box
4060, 61040 Tel Aviv (IL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SHELL FOR BALLISTIC HELMET

(57) Abstract: A shell for ballistic helmet formed from a plurality of paraaramide fabric layers such as KEVLAR-KM2[®], and bonding resin. All fabric layers have areal density less than 200g/m², preferably part of them have areal density less than 160g/m². The number of paraaramide layers is greater than 28, preferably 38 and more. The bonding resin constitutes less than 12% of the shell weight. The shell has average thickness less than 6.5 mm and average areal density less than 7.5 Kg/m². A method for the production of such shells includes pressing and bonding the plurality of layers at pressure equal to or above 150Kg/cm², preferably above 300Kg/cm².